

Class	150 lbs.	300 lbs.
Materials	ASTM A 197.87	ASTM A 197.87
Dimensions	ANSI B 16.3-1998, B 16.14-1991	ANSI B 16.39.1998, B 16.14-1991
Union Dimensions	ASME B16.39.1998, DIN En 10242	ASME B16.39.1998,
Threads	ANSI / ASME B 1.20.1 1983, ISO 7.1.1994	ANSI / ASME B 1.20.1-1983
Tensile Strength	≥ 40,000 psi (28.4 kgf/mm ²)	≥ 40,000 psi (28.4 kgf/mm ²)
Elongation	≥ 5%	≥ 5%
Zinc Coating	ASTM A 153/A 153M 1998	ASTM A 153/A 153M 1998
Working Pressure	150 psing at 350°F	300 psing at 550°F